

CrysticROOF Premier Resin

Introduction

CrysticROOF Premier Resin is a low styrene emission, pre-accelerated, orthophthalic polyester resin, which rapidly wets out reinforcements. It has been specifically designed to be used with CrysticROOF Premier FR Topcoat by BBA Approved Contractors for flat roofing applications. It is not suitable for boat construction, chemical resistance or mouldings in contact with food products.

Product Characteristics

Formulation CrysticROOF Premier Resin should be stirred well by hand, or with a low shear mixer to avoid aeration, and then allowed to stand to regain thixotropy. CrysticROOF Premier Resin requires only the addition of catalyst to start the curing reaction. The recommended catalyst is Catalyst M (or Butanox M50), which should be added at 1% into the resin. The catalyst should be thoroughly incorporated into the resin with a low shear mechanical stirrer where possible.

Pot Life

Temperature	Pot Life In Minutes with 1% Catalyst M
15°C	42
20°C	22
25°C	17

Ideally the resin and ambient temperature should be at, or above, 15 °C before curing is carried out. Lower temperatures will lengthen the cure time considerably. The level of catalyst can be increased to 2% to assist the cure at reduced temperatures. The environmental conditions should be dry and with no imminent rain forecast. The substrate should also be dry before application begins in order to ensure a good bond.

Application

CrysticROOF Premier Resin is designed for hand laminating and would normally be used with chopped strand mat.

Additives

The addition of filler or pigments can adversely affect the hardening of the resin. Users should evaluate the effect of any potential additives before use.

Typical Properties

The following tables give the minimum expected properties of CrysticROOF Premier Resin when tested in accordance with BS 2782.

Property		Liquid Resin
Appearance		Greenish Blue
Viscosity at 25°C		Thixotropic
Specific Gravity at 25°C		1.12
Volatile Content	%	43
Stability in the dark at 20°C	Months	*
Geltime at 25°C using 1% Catalyst M (or Butanox M50)	Minutes	17

*From date of delivery

Property		Fully Cured* Resin (Unfilled Casting)
Barcol Hardness (Model GYZJ 934-1)		42
Deflection Temperature under load † (1.80 MPa)	°C	67
Water Absorption 24 hours at 23°C	Mg	15
Tensile Strength	MPa	50
Tensile Modulus	MPa	3800
Elongation at Break	%	1.5

* Curing Schedule - 24 hrs @ 20°C, 3 hrs @ 80°C

† Curing Schedule - 24 hrs @ 20°C, 5 hrs @ 80°C, 3 hrs @ 120°C

Property		CSM** Laminate
Tensile Strength	MPa	98
Tensile Modulus	MPa	7600
Flexural Strength	MPa	190
Flexural Modulus	MPa	7400
Elongation at Break	%	1.7

**Made with 4 layers 450g/m² PB CSM

Curing Schedule - 24 hrs @ 20°C, 16hrs @ 40°C.

Storage

CrysticROOF Premier Resin should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20 °C where practical, but should not exceed 30 °C. Ideally, containers should be opened only immediately prior to use. Where they have to be stored outside, it is recommended that they are kept in a horizontal position to avoid the possible ingress of water.

Packaging

CrysticROOF Premier Resin is supplied in 20kg containers.

Health & Safety

Please see separate Material Safety Data Sheet.

Version 2: May 2014

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com