

CrysticROOF Topcoat

ISO Topcoat for Brush or Roller Application

Introduction

CrysticROOF Topcoat is a pre-accelerated isophthalic topcoat. It is has been formulated for brush or roller application.

The Scott Bader Technical Service Department is able to provide information and advice relating to the use of composites products in a wide range of markets and applications.

Applications

CrysticROOF Topcoat is suitable for use in general flat roofing applications.

Features and Benefits

CrysticROOF Topcoat has been developed to ensure good intrinsic weathering properties and good water resistance. The robust formulation ensures the topcoat is suitable for use in a wide range of application conditions.

Product Characteristics

Ideally the CrysticROOF Topcoat and ambient temperature should be at, or above, 15 °C before curing is carried out. Lower temperatures will lengthen the cure time considerably. Stir well by hand, or with a low shear mixer to avoid aeration, and then allow to stand to regain thixotropy. CrysticROOF Topcoat requires only the addition of a catalyst to start the curing reaction. The recommended catalyst is Catalyst M (or Butanox M50), which should be added at 2 % into the gelcoat. (Please consult our Technical Service Department if other catalysts are to be used). The catalyst should be thoroughly incorporated into the topcoat, with a low shear mechanical stirrer where possible. Please consult our Technical Service Department for further application advice.

For normal use, the application of CrysticROOF Topcoat should be controlled to 0.4 - 0.5 mm (0.015 - 0.020 inch) wet film thickness. As a guide, approximately 650-800 g/m² of topcoat mixture (depending on pigment) will give the required thickness when evenly applied. CrysticROOF Topcoat should be applied to clean and dry surfaces and when used outside when rain is not likely to fall within 2 hours of application.

Properties

Typical Properties

The following table gives typical liquid properties of CrysticROOF Topcoat when tested in accordance with Scott Bader test methods.

Property	Method	Typical Result
Viscosity, 25 °C 0.6s-1	3.41	250-350 Poise
Viscosity, 25 °C 4500s-1	3.6	4-8 Poise
Specific gravity @ 25 °C	-	1.7
Stability in the dark @ 20 °C	-	5 Months*
Geltime 20 °C 2% Catalyst M (Butanox M50)	5.25	7-12 Minutes

*From date of delivery

Storage


CrysticROOF Topcoat should be stored in the original containers which must be kept closed and airtight. It is recommended that the storage temperature should be less than 20°C to achieve maximum storage life.

Packaging

CrysticROOF Topcoat is supplied in 20kg and 225kg containers.

Health And Safety

Please refer to Material Safety Data Sheet.



Version 2: July 2014

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com